

AMENDMENTS TO THE CLAIMS

Please amend the Claims as follows. Insertions are shown underlined while deletions are ~~struck through~~.

1 (currently amended): A method for manufacturing a homeotropic alignment liquid crystal film, comprising the steps of:

91 ~~wherein~~coating a side chain type liquid crystal polymer comprising a monomer unit (a) containing a liquid crystalline fragment side chain and a monomer unit (b) containing a non-liquid crystalline fragment side chain ~~is coated on~~ a substrate on which a vertical alignment film is not ~~prepared~~formed, said liquid crystal polymer being capable of homeotropic alignment solely by heating;

after the substrate is coated with the liquid crystal polymer which is in a liquid crystal state, homeotropically aligning the liquid crystal polymer by heating; and

fixing the liquid crystal polymer is fixed while maintaining a ~~resulting homeotropic alignment state after~~of the liquid crystal polymer ~~is homeotropically aligned in liquid crystal state.~~

2 (currently amended): The method ~~for manufacturing a homeotropic alignment liquid crystal film according to claim 1, wherein a material of a~~said substrate is a polymer, glass or metal.

3 (canceled)

4 (canceled)

5 (canceled)

6 (canceled)

7 (canceled)

8 (canceled)

9 (currently amended): A method for manufacturing a homeotropic alignment liquid crystal film, comprising the steps of:

~~wherein the~~coating a homeotropic alignment liquid crystalline composition according to claim 7 is coated on a substrate on which a vertical alignment film is not ~~prepared~~formed, said composition being capable of homeotropic alignment solely by heating and comprising a side chain type liquid crystal polymer and a photopolymerizable liquid crystal compound;

~~subsequently~~after the substrate is coated with the liquid crystalline composition which is in a liquid crystal state, ~~homeotropically aligning the homeotropic alignment liquid crystalline composition is homeotropically aligned in liquid crystal state by heating;~~

fixing a resulting homeotropic alignment state of the liquid crystalline composition;
 and

~~is applied~~applying an optical irradiation to the liquid crystalline composition after fixed in a state of an alignment state being maintained to fix the liquid crystalline composition.


10 (currently amended): The method ~~for manufacturing a homeotropic alignment liquid crystal film~~ according to claim 9, wherein a material of the substrate is a polymer substance, glass or metal.

11 (canceled)

12 (canceled)


13 (canceled)

14 (new): The method according to claim 1, wherein said monomer unit (a) comprises a monomer unit represented by the following formula:




wherein R¹ is a hydrogen atom or a methyl group, a is a positive integer of 1 to 6, X is -CO₂- group or -OCO- group, R² is a cyano group, an alkoxy group with 1 to 6 carbon, fluoro group or alkyl group with 1 to 6 carbon, and b and c are integers of 1 or 2 respectively; and

said monomer unit (b) comprises a monomer unit represented by the following formula:




wherein R³ is a hydrogen atom or a methyl group, R⁴ is an alkyl group with 1 to 22 carbon, a fluoroalkyl group with 1 to 22 carbon, or a monomer unit represented by the following formula:



wherein d is a positive integer of 1 to 6, and R⁵ is an alkyl group with 1 to 6 carbon.


15 (new): The method according to claim 1, wherein said heating is conducted at 70°C - 200°C.

16 (new): The method according to claim 9, wherein said side chain type liquid crystal polymer comprises a monomer unit (a) containing liquid crystalline fragment side chain and a monomer unit (b) containing non-liquid crystalline fragment side chain, said monomer unit (a) comprising a monomer unit represented by the following formula:




wherein R¹ is a hydrogen atom or a methyl group, a is a positive integer of 1 to 6, X is -CO₂- group or -OCO- group, R² is a cyano group, an alkoxy group with 1 to 6 carbon, fluoro group or alkyl group with 1 to 6 carbon, and b and c are integers of 1 or 2 respectively; and

21 said monomer unit (b) comprising a monomer unit represented by the following formula:



wherein R³ is a hydrogen atom or a methyl group, R⁴ is an alkyl group with 1 to 22 carbon, a fluoroalkyl group with 1 to 22 carbon, or a monomer unit represented by the following formula:



wherein d is a positive integer of 1 to 6, and R⁵ is an alkyl group with 1 to 6 carbon.

17 (new): The method according to claim 9, wherein said heating is conducted at 70°C - 200°C.